

SUMMITECH LATEKSOWE SZORSTKOWANE RF4 SB

Chemical Name (CAS Number)	Breakthrough Time (minutes)	Protection Index
1-Methoxy-2-Propanol (107-98-2)	-	-
1-Methoxy-2-Propylacetate (108-65-6)	-	-
Acrylic Acid (79-10-7)	-	-
Acrylonitrile (107-13-1)	-	-
Allyl Alcohol (107-18-6)	-	-
Ammonia Hydroxide 25% (1336-21-6)	-	-
Benzene (71-43-2)	-	-
Benzoylchloride (98-88-4)	-	-
Biphenol A (80-05-7)	-	-
Bromopropionic Acid (590-92-1)	-	-
Butyl Alcohol (71-36-6)	-	-
Butylglycol (111-76-2)	-	-
Carbon Disulfide (75-15-0)	-	-
Carbon Tetra Chloride (56-23-5)	-	-
Chloroform (865-49-6)	-	-
Coal Tar (8007-45-2)	-	-
Crude Oil (60308-34-9)	-	-
Dibutyl Phtalate (84-74-2)	-	-
Distillate Hydrotreated light (64742-47-8)	-	-
DOP (117-84-0)	-	-
Ethylbenzene (96-33-3)	-	-
Ethylene Glycol (107-21-1)	-	-
Ethylglycol Acetate (111-15-9)	-	-
Freon TF (76-13-1)	-	-
Gamma Butyrolactone (96-48-0)	-	-
Glutaraldehyde 50% (C111-30-6)	-	-
Glycol (111-46-6)	-	-
Hexamethyldisilazane (999-97-3)	-	-
Hydrofluoric Acid 14% (7664-39-3)	-	-
Isophorone (78-59-1)	-	-
Methyl Acrylate (CAS)	-	-
Methyl Isobutyl Ketone (108-10-1)	-	-
Methyl-T-Butyl Ether (1634-04-4)	-	-
Methylamine 40% (74-89-5)	-	-
Mineral Oil (CAS)	-	-
Monochlorobenzene (108-90-7)	-	-
Monoethanolamine (141-43-5)	-	-
Naptha Desulfurize Heavy (64742-82-1)	-	-
Naptha Hydrotreated Light (64742-49-0)	-	-
Naptha VM&P (8030-30-6)	-	-
Paraffin Oil (8012-95-1)	-	-
Peracetic Acid 39% (79-21-0)	-	-
Perchloroethylene (127-18-4)	-	-
Pinerazine Aq Solution (110-85-0)	-	-
Potassium Phosphate (7758-11-4)	-	-
Propionitrile (107-12-0)	-	-

Propylene Glycol (57-55-6)	-	-
Pyridine (110-86-1)	-	-
Sodium Carbonate (497-19-8)	-	-
Sodium Phosphate (7601-54-9)	-	-
Sodium Sulphate (7757-82-6)	-	-
Stoddard Solvent (8052-41-3)	-	-
Styrene (100-42-5)	-	-
Tetrahydrothiophene (110-01-0)	-	-
Thionylchloride (7719-09-7)	-	-
Trichloroethylene (79-01-6)	-	-
Tricresyl phosphate (1330-78-5)	-	-
Triethanolamine (102-71-6)	-	-
Triethylamine (121-44-8)	-	-
White Spirit (64742-88-7)	-	-
Calcium Nitrate (10124-37-5)	> 480	6
Citric Acid (Pure) (77-92-9)	> 480	6
Cyclo-Hexanol (108-93-0)	> 480	6
Ethanol (64-17-5)	> 480	6
Ethyl Glycol (107-21-2)	> 480	6
Formaldehyde 30% (50-00-0)	> 480	6
Glycerine (56-81-5)	> 480	6
Iso-Propanol (67-63-0)	> 480	6
Maleic Acid (110-16-7)	> 480	6
Nitric Acid 20% (7697-37-2)	> 480	6
Oleic Acid (112-80-1)	> 480	6
Oxalic Acid (Pure) (144-62-7)	> 480	6
Phosphoric Acid 85% (7664-38-2)	> 480	6
Propanol (71-23-8)	> 480	6
Sodium Hydroxide 40% (1310-73-2)	> 480	6
Calcium Chloride (10043-52-4)	> 240	5
Hydrochloric Acid 30% (7647-01-0)	> 240	5
Hydrogen Peroxide 31% (7722-84-1)	> 240	5
Potassium Nitrate (7757-79-1)	> 240	5
Sodium Nitrate (7631-99-4)	> 240	5
Sulphuric Acid 98% (7664-93-9)	> 240	5
Acetic Acid 50% ()	> 120	4
Acetic Acid 99% (64-19-7)	> 120	4
Ammonia 10% (1336-21-6)	> 120	4
Dimethyl Sulfoxide (67-68-5)	> 120	4
Formic Acid 90% (64-18-6)	> 120	4
Ammonia Acetate (631-61-8)	> 60	3
Kerosene (8008-20-6)	> 60	3
Phenol (108-95-2)	> 60	3
Sodium Hypochloride 10% (7681-52-9)	> 60	3
Ammonia Chloride (12125-02-9)	> 30	2
Ammonia Nitrate (6484-52-2)	> 30	2
Calcium Hydroxide (1305-62-0)	> 30	2
Calcium Hypochlorite (7778-54-3)	> 30	2
Cyclo-Hexane (110-82-7)	> 30	2
Dimethylformamide (68-12-2)	> 30	2

Iso-Octane (540-84-1)	> 30	2
Methanol (67-56-1)	> 30	2
Acetonitrile (75-05-8)	> 10	1
Butyl Acetate (123-86-4)	> 10	1
Cyclohexanone (108-93-0)	> 10	1
Diesel Oil (68334-30-5)	> 10	1
Ethylamine (75-04-7)	> 10	1
Gasoline (8006-61-9)	> 10	1
Heptane (142-82-5)	> 10	1
Methylethylketone (MEK) (78-93-3)	> 10	1
N-Methyl-2-Pyrrolidone (872-50-4)	> 10	1
Nitrobenzene (98-95-3)	> 10	1
Octane (111-65-9)	> 10	1
Propylacetate (109-60-4)	> 10	1
Acetone (67-64-1)	< 10	0
Diethylamine (109-89-7)	< 10	0
Diethylether (60-29-7)	< 10	0
Ethyl Acetate (141-78-6)	< 10	0
Hexane (110-54-3)	< 10	0
Methyl Methacrylate (80-62-6)	< 10	0
Methylene Chloride (75-09-2)	< 10	0
Tetrahydrofuran (THF) (109-99-9)	< 10	0
Toluene (108-88-3)	< 10	0
Xylene (1330-20-7)	< 10	0