

SUMMITECH POLSTARITTA GUMOWA

FLOKOWANA PRO. EF-F-06

Chemical Name (CAS Number)	Breakthrough Time (minutes)	Protection Index
DOP (117-84-0)	> 480	6
Ethyl Glycol (107-21-2)	> 480	6
Ethylene Glycol (107-21-1)	> 480	6
Formaldehyde 30% (50-00-0)	> 480	6
Glutaraldehyde 50% (C111-30-6)	> 480	6
Glycerine (56-81-5)	> 480	6
Glycol (111-46-6)	> 480	6
Hydrofluoric Acid 14% (7664-39-3)	> 480	6
Hydrogen Peroxide 31% (7722-84-1)	> 480	6
Maleic Acid (110-16-7)	> 480	6
Monoethanolamine (141-43-5)	> 480	6
Oleic Acid (112-80-1)	> 480	6
Oxalic Acid (Pure) (144-62-7)	> 480	6
Paraffin Oil (8012-95-1)	> 480	6
Phosphoric Acid 85% (7664-38-2)	> 480	6
Pinerazine Aq Solution (110-85-0)	> 480	6
Potassium Phosphate (7758-11-4)	> 480	6
Propylene Glycol (57-55-6)	> 480	6
Sodium Carbonate (497-19-8)	> 480	6
Sodium Hydroxide 40% (1310-73-2)	> 480	6
Sodium Hypochloride 10% (7681-52-9)	> 480	6
Sodium Phosphate (7601-54-9)	> 480	6
Sodium Sulphate (7757-82-6)	> 480	6
Tricresyl phosphate (1330-78-5)	> 480	6
Triethanolamine (102-71-6)	> 480	6
Cyclo-Hexanol (108-93-0)	> 240	5
Dimethyl Sulfoxide (67-68-5)	> 120	4
Formic Acid 90% (64-18-6)	> 120	4
Gamma Butyrolactone (96-48-0)	> 120	4
Nitric Acid 20% (7697-37-2)	> 120	4
Ethanol (64-17-5)	> 60	3
Hydrochloric Acid 30% (7647-01-0)	> 60	3
Iso-Propanol (67-63-0)	> 60	3
Potassium Nitrate (7757-79-1)	> 60	3
Propanol (71-23-8)	> 60	3
Sodium Nitrate (7631-99-4)	> 60	3
Dimethylformamide (68-12-2)	> 30	2
Kerosene (8008-20-6)	> 30	2
Methanol (67-56-1)	> 30	2
Phenol (108-95-2)	> 30	2
Sulphuric Acid 98% (7664-93-9)	> 30	2
Cyclo-Hexane (110-82-7)	> 10	1
Diethylamine (109-89-7)	> 10	1
Hexane (110-54-3)	> 10	1

Octane (111-65-9)	> 10	1
Peracetic Acid 39% (79-21-0)	> 10	1
Crude Oil (60308- _34-9)	< 10	0
Cyclohexanone (108-93-0)	< 10	0
Dibutyl Phtalate (84-74-2)	< 10	0
Diesel Oil (68334- _30-5)	< 10	0
Diethylether (60-29-7)	< 10	0
Distillate Hydrotreated light (64742- _47-8)	< 10	0
Ethyl Acetate (141-78-6)	< 10	0
Ethylamine (75-04-7)	< 10	0
Ethylbenzene (96-33-3)	< 10	0
Ethylglycol Acetate (111-15-9)	< 10	0
Freon TF (76-13-1)	< 10	0
Gasoline (8006-61-9)	< 10	0
Heptane (142-82-5)	< 10	0
Hexamethyldisilazane (999-97-3)	< 10	0
Iso-Octane (540-84-1)	< 10	0
Isophorone (78-59-1)	< 10	0
Methyl Acrylate (CAS)	< 10	0
Methyl Isobutyl Ketone (108-10-1)	< 10	0
Methyl Methacrylate (80-62-6)	< 10	0
Methyl-T-Butyl Ether (1634-04-4)	< 10	0
Methylamine 40% (74-89-5)	< 10	0
Methylene Chloride (75-09-2)	< 10	0
Methylethylketone (MEK) (78-93-3)	< 10	0
Mineral Oil (CAS)	< 10	0
Monochlorobenzene (108-90-7)	< 10	0
N-Methyl-2-Pyrrolidone (872-50-4)	< 10	0
Naptha Desulfurize Heavy (64742- _82-1)	< 10	0
Naptha Hydrotreated Light (64742- _49-0)	< 10	0
Naptha VM&P (8030-30-6)	< 10	0
Nitrobenzene (98-95-3)	< 10	0
Perchloroethylene (127-18-4)	< 10	0
Propionitrile (107-12-0)	< 10	0
Propylacetate (109-60-4)	< 10	0
Pyridine (110-86-1)	< 10	0
Stoddord Solvent (8052-41-3)	< 10	0
Styrene (100-42-5)	< 10	0
Tetrahydrofuran (THF) (109-99-9)	< 10	0
Tetrahydrothiophene (110-01-0)	< 10	0
Thionylchloride (7719-09-7)	< 10	0
Toluene (108-88-3)	< 10	0
Trichloroethylene (79-01-6)	< 10	0
Triethylamine (121-44-8)	< 10	0
White Spirit (64742- _88-7)	< 10	0
Xylene (1330-20-7)	< 10	0